

VIC ASH

ORIGIN	New South Wales, Victoria and Tasmania
SPECIES TYPE	Hardwood
SUSTAINABILITY	Available in PEFC/AFS with a Chain of Custody for Green Star points. On request only.
AVAILABILITY	Readily available
DURABILITY	Class 3 out of ground (7-15 years)
HARDNESS	Janka 4.9kN
DENSITY (DRY)	660kg/m ³ (at 12% moisture content)
MOVEMENT	Low tangential 4.5 (shrinkage across the board width)
LYCTID SUSCEPTIBILITY	Not susceptible in Victoria, susceptible in Tasmania and New South Wales
TERMITE RESISTANCE	Not resistant
FIRE	Satisfies BCA C1.10a Group 3 (slightly combustible). Does NOT comply with BAL under AS3959-2009. Ignitibility: 14, Spread of Flame Index: 8, Smoke Developed Index: 3, Critical Radiance Flux Higher and Lower: >2.2 and 4.5kW/m ² , Smoke Development Rate: <750, Average Extinction Area: <250
LENGTHS	Average length 2.7m - 3.0m
TYPICAL APPLICATIONS	Internal cladding and battens

BOTANICAL NAME: DELEGATENSIS & E. REGNANS

Pale to pink straw, Victorian Ash features a moderately course texture and has a predominately straight grain, although it may be wavy in parts resulting in a fiddle back appearance. It will provide a light, creamy-coloured timber for appearance applications. Excellent for taking stains.

TYPICAL CHARACTERISTICS



August 2017 | 01220717



1800 008 828
sculptform.com.au | support@sculptform.com.au

REFERENCES: Wood Solutions (www.woodsolutions.com.au); Australian Standards AS5604-2005; Wood in Australia by Keith R. Bootle 2002 ISBN 0 07 451047 9.; Australian Standards AS 3959-2009

NOTE: To maintain currency, this document is periodically reviewed, and new editions are published. Between editions, amendments may be issued, so its important that readers assure themselves they are using a current document. We welcome suggestions for improvement, and encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email support@sculptform.com.au or phone 1800 008 828.

Available in PEFC/
Responsible Wood with
a Chain of Custody for
Green Star points. On
request only.

